



## GEOGREEN® PEN 'REPLICATED GRASS'

GeoGreen® PEN is a dimensionally stable 'Replicated Grass' consisting of a multi-layer, Matrix primary backing, with a urethane secondary backing which is heat activated to permanently lock fiber tufts in place. GeoGreen PEN is tufted with a polyethylene face yarn and a texturized thatch. The yarn is tufted with a 3/8" gauge (stitch separation) and a maximum filament height of 1 1/8".

TYPICAL PROPERTIES	U.S.	TEST METHOD
Yarn Face Weight (oz per square yard)	69 ounces	ASTM D5848
Yarn Thickness	200 Micron	ASTM D5848
Tufting Gauge	3/8 inch	Empirical
Pile Height	1 1/8"	Empirical
Tuft Bind	8 pounds	ASTM D1335
Grab Tear Strength	250/250 (X & Y)	ASTM D5034
Primary Backing (two layer)	Tencate K29	Empirical
Secondary Backing	20 oz urethane	Empirical
Total Weight (oz per square yard)	95 ounce (without infill)	ASTM D5848
In-fill Depth	NONE	
In-fill Material	NONE	
Permeability	64.5 inches per hour	ASTM D4716
Flammability (PILL) Test	Pass	ASTM D2859



## "TURN KEY" SPORTS SURFACING

GeoSurfaces® is one of the few companies in the USA that offers in-house "turn key" sports lighting and sports surfacing. We are a licensed Professional Construction Firm, Electrical Firm, and Construction Manager that can offer complete construction and installation of FIFA, IAAF and ITF Approved Surfaces.